



170021183991



TESTING
CNAS L6011

Test Report

BJZ(2018) 0377

Name: Ballistic Panel

Type: SA-35

Test Sort: Commission Test

Client: YONGKANG LONGKUI NEW
MATERIAL CO., LTD.



Date: May 8, 2018

Test Center of Ordnance and

Equipment Research Institute,

China Ordnance and Equipment Group

Quality Supervision and Inspection

Center for Special Production of

China Ordnance and Equipment

Notice

- 1 The test-report invalidate if no special test-stamp.
- 2 The test-report invalidate if no signature of Editor, Censor or Approver.
- 3 The test-report invalidate if it is altered and copied.
- 4 It should be demurred within fifteen days after received the test-report. Not accept if expired.
- 5 The test-report is just answer for the test sample.

Add Box 1023 ,Chang Ping , Bei Jing
Tel 86-010-80190337、 0348
Fax 80190340
Post 102202

Test Report

BJZ(2018)0377

Page 1 of 4

Name	Ballistic Panel	Type	SA-35
Client	YONGKANG LONGKUI NEW MATERIAL CO., LTD.	Client Principal	Shi Zheng Yin
Address	NO. 366, Kechuang Road, The Economic Development Zone, Yongkang City, Zhejiang, China	Telephone	0579-8715313
Manufacturer	YONGKANG LONGKUI NEW MATERIAL CO., LTD.	Test Sort	Commission Test
Test Date	Apr. 24, 2018	Brand	LONGKUI
Lot Number	180411-5	Sample Quantity	1
Serial Number	YP180424-8	Sample State	Good
Standard	NIJ Standard-0101.04 Ballistic Resistance of Personal Body Armor		
Test item	Bulletproof Performance		
Test Conclusion	<p>Type SA-35 ballistic panel, which is provided by YONGKANG LONGKUI NEW MATERIAL CO., LTD, has been tested by ball firing at normal temperature. The bulletproof performance conforms to the requirements of level IIIA of NIJ Standard-0101.04 Ballistic Resistance of Personal Body Armor.</p> <p>See the table and Picture 1-2.</p>		
Remarks			
Editor: Gao Jie	Censor: Zhao Hong	Approver:	Zhao Hong

Test Report

BJZ(2018)0377

Page 2 of 4

Test place, environment (special requirement of environment) and test equipments	
Test place	Quality Supervision and Inspection Center for Special Production of China Ordnance Equipment
Test environment (special requirement of environment)	/
	Indoor: temperature 22℃, humidity 49%RH
Test equipments	/
	Universal standard Measure Tools Ballistic Analytic System (No.329000001) Electro- balance (No.CSJL-00005) Testing weapon: 9mm Uzi Sub-machine gun Testing ammunition: 9mm Parabellum pistol cartridge
Character & Structure of sample	The sample is made of 36 layers of PE and 4.5mm foam.

Test Table of Type SA-35 Ballistic Panel


BJZ(2018) 0377

Sample Number	Ballistic Panel Weight (kg)	Protected Area (m ²)	Sample Condition	Shooting Distance (m)	Angle of Incidence	Shooting Sequence	Muzzle Velocity (m/s)	Penetration Requirement (mm)	BFS Depth Measured Value (mm)				
YP180424-8	0.82	0.16	Normal Temperature	5	0°	1	435	NP	25.1				
						2	437	NP	27.4				
						3	442	NP	25.4				
					Left 30°	4	439	NP	19.8				
						5	440	NP	13.2				
						6	442	NP	18.7				
					≤ 44.0								

Test Report

BJZ(2018) 0377

Page 4 of 4



Picture 1 Impact Side



Picture 2 Backing Material

